

Attachment to Baker C-1 (API # 15-129-21919)

Cement & Additives

String	Type	# of Sacks Used	Type and Percent Additives
Surface	A-Con	Lead: 490	3% CC, 1/2# Cellflake, 0.2% WCA1
	Prem Plus	Tail: 200	2% CC, 1/4# Cellflake
Production	A-Con	Lead: 80	2% CC, 1/4# Cellflake, 0.2% WCA1
	50-50 Poz	Tail: 130	5% W-60, 10% Salt, 0.6% C-15, 1/4# Defoamer, 5# Gilsonite