

Attachment to Steckel Farms A-1 (API # 15-129-21921)

Cement & Additives

String	Type	# of Sacks Used	Type and Percent Additives
Surface	A-Con	Lead: 490	3% CC, 1/2# Cellflake, 0.2% WCA1
	Prem Plus	Tail: 200	2% CC, 1/4# Cellflake
Production	A-Con	Lead: 100	3%CC, 1/2# Cellflake, 0.2 WCA-1
	50-50 Poz	Tail: 155	5% W-60, 10% Salt, 0.6% C-15, 1/4# Defoamer, 5# Gilsonite