

**Attachment to Sullivan D-1 (API # 15-067-21717)**

**Cement & Additives**

String	Type	# of Sacks Used	Type and Percent Additives
Surface	A-Con	Lead: 480	3% CC, 1/2# Cellflake, 0.2% WCA1
	Prem Plus	Tail: 200	2% CC, 1/4# Cellflake
Production	A-Con	Lead: 230	3% CC, 1/4# Cellflake, 0.2% WCA1
	50-50 Poz	Tail: 140	5% Cal-Seal, 10% Salt, 0.6% C-15, 1/4# Defoamer, 5# Gilsonite