

**Attachment to Strackeljohn A-1 (API # 15-055-22101)**

**Cement & Additives**

| String     | Type      | # of Sacks Used | Type and Percent Additives                                   |
|------------|-----------|-----------------|--|
| Surface    | A-Con     | Lead: 440       | 3% CC, 1/2# Cellflake, 0.2% WCA1                             |
|            | Prem +    | Tail: 160       | 2% CC, 1/4# Cellflake  |
| Production | 50-50 Poz | 125             | 5% W-60, 10% Salt, 0.6% C-15,<br>1/4# Defoamer, 5# Gilsonite |