

**Attachment to Elizabeth A. Cox #5 (API 15-081-21942)**

**Cement & Additives**

| String     | Type      | # of Sacks Used | Type and Percent Additives                                |
|------------|-----------|-----------------|---|
| Surface    | A-Con     | Lead: 335       | 3% CC, 1/2# Cellflake, 0.2% WCA1                          |
|            | Class C   | Tail: 200       | 2% CC, 1/4# Cellflake                                     |
| Production | 50-50 Poz | 230             | 5% W-60, 10% Salt, 0.6% C-15, 1/4# Defoamer, 5# Gilsonite |