

Attachment to Longbotham #6 (API # 15-081-21960)

Cement & Additives

String	Type	# of Sacks Used	Type and Percent Additives
Surface	A-Con	Lead: 340	3% CC, 1/4# Cellflake, 0.2% WCA1
	Prem +	Tail: 230	2% CC, 1/4# Cellflake
Production	50-50 Poz	250	5% W-60, 10% Salt, 0.6% C-15, 1/4# Defoamer, 5# Gilsonite 1/4# Polyflake
Production Liner	50-50 Poz	165	5% W-60, 10% Salt, 0.6% C-15, 1/4# Defoamer, 5# Gilsonite 1/4# Polyflake