



<b>JOB SUMMARY</b>			PROJECT NUMBER <b>SOK1272</b>	TICKET DATE <b>03/05/12</b>
COUNTY <b>Comanche</b>	State <b>Oklahoma</b>	COMPANY <b>Sandridge Exp and Production</b>	CUSTOMER REP <b>Roger Barber</b>	
LEASE NAME <b>Larry</b>	Well No. <b>1-30H</b>	JOB TYPE <b>Surface</b>	EMPLOYEE NAME <b>Johnny Breeze</b>	

EMP NAME					
Johnny Breeze					
Daniel Wells					
Flo Helkena					
Scott Woods					

Form. Name \_\_\_\_\_ Type: \_\_\_\_\_  
 Packer Type \_\_\_\_\_ Set At 0  
 Bottom Hole Temp. 80 Pressure \_\_\_\_\_  
 Retainer Depth \_\_\_\_\_ Total Depth 1000

Date	Called Out <b>3/5/2012</b>	On Location <b>3/5/2012</b>	Job Started <b>3/5/2012</b>	Job Completed <b>3/5/2012</b>
Time	<b>05:00</b>	<b>11:30</b>	<b>16:56</b>	<b>18:30</b>

Tools and Accessories		
Type and Size	Qty	Make
Auto Fill Tube	0	IR
Insert Float Val	0	IR
Centralizers	0	IR
Top Plug	1	IR
HEAD	1	IR
Limit clamp	0	IR
Weld-A	0	IR
Texas Pattern Guide Shoe	0	IR
Cement Basket	0	IR

Well Data						
New/Used	Weight	Size	Grade	From	To	Max. Allow
Casing	36.0	9 5/8		Surface	991	1,500
Liner						
Liner						
Tubing		0				
Drill Pipe						
Open Hole		12 1/4"		Surface	1,000	Shots/Ft.
Perforations						
Perforations						
Perforations						

Materials			
Mud Type	WBM	Density	9 Lb/Gal
Disp. Fluid	Fresh Water	Density	8.33 Lb/Gal
Spacer type	resh Water BBL.		10 8.33
Spacer type	BBL.		
Acid Type	Gal.		%
Acid Type	Gal.		%
Surfactant	Gal.		ln
NE Agent	Gal.		ln
Fluid Loss	Gal/Lb		ln
Gelling Agent	Gal/Lb		ln
Fric. Red.	Gal/Lb		ln
MISC.	Gal/Lb		ln


Hours On Location		Operating Hours		Description of Job
Date	Hours	Date	Hours	
3/5	6.0	3/5	4.0	Surface
Total	6.0	Total	4.0	

Perfpac Balls \_\_\_\_\_ Qty. \_\_\_\_\_  
 Other \_\_\_\_\_  
 Other \_\_\_\_\_  
 Other \_\_\_\_\_  
 Other \_\_\_\_\_  
 Other \_\_\_\_\_

Pressures			
MAX	1,500 PSI	AVG	200
Average Rates in BPM			
MAX	8 BPM	AVG	5
Cement Left in Pipe			
Feet	42	Reason	SHOE JOINT

Cement Data						
Stage	Sacks	Cement	Additives	W/Rq.	Yield	Lbs/Gal
1	440	O-Tex Lite Standard	(6%Gel) 2% Calcium Chloride - 1/4 lb/sk Cellflake - 0.5% C-41P	10.88	1.84	12.70
2	180	Standard	2% Calcium Chloride - 1/4 lb/sk Celloflake	5.20	1.18	15.60
3	100	Standard	2% Calcium Chloride on the side	5.20	1.18	15.60

Summary			
Preflush	<input type="text" value="10.00"/>	Type:	FRESH WATER
Breakdown	MAXIMUM 1,500 PSI	Load & Bkdn:	Gal - BBI N/A
	Lost Returns-N	Excess /Return	BBI 80
	Actual TOC	Calc. TOC:	SURFACE 73
Average	Bump Plug PSI: 980	Final Circ. PSI:	350
ISIP	5 Min. 10 Min. 15 Min.	Cement Slurry: BBI	182.0
		Total Volume	BBI 265.02

CUSTOMER REPRESENTATIVE  SIGNATURE

<b>JOB SUMMARY</b>			PROJECT NUMBER <b>SOK1288</b>	TICKET DATE <b>03/12/12</b>
COUNTY <b>Comanche</b>	State <b>Kansas</b>	COMPANY <b>Sandridge Exp and Prod</b>	CUSTOMER REP <b>Roger Barber</b>	
LEASE NAME <b>Larry</b>	Well No. <b>1-30H</b>	JOB TYPE <b>Intermediate</b>	EMPLOYEE NAME <b>Johnny Breeze</b>	

EMP NAME					
Johnny Breeze					
Scott Woods					
Fjo Helkena					
Emmit Brock					

Form. Name \_\_\_\_\_ Type: \_\_\_\_\_  
Packer Type \_\_\_\_\_ Set At **4,111'**  
Bottom Hole Temp. **0** Pressure \_\_\_\_\_  
Retainer Depth \_\_\_\_\_ Total Depth **5,415'**

Date	Called Out <b>3/11/2012</b>	On Location <b>3/11/2012</b>	Job Started <b>3/12/2012</b>	Job Completed <b>3/12/2012</b>
Time	<b>0800</b>	<b>1330</b>	<b>0229</b>	<b>0430</b>

Tools and Accessories		
Type and Size	Qty	Make
Auto Fill Tube	0	IR
Insert Float Val	0	IR
Centralizers	0	IR
Top Plug	1	IR
HEAD	1	IR
Limit clamp	0	IR
Weld-A	0	IR
Texas Pattern Guide Shoe	0	IR
Cement Basket	0	IR

Well Data							
	New/Used	Weight	Size	Grade	From	To	Max. Allow
Casing		26.0	7		Surface	5,573	5,000
Liner							
Liner							
Tubing							
Drill Pipe							
Open Hole			8 3/4"		Surface	5,568	Shots/Ft.
Perforations							
Perforations							
Perforations							

Materials			
Mud Type	WBM	Density	<b>9.1</b> Lb/Gal
Disp. Fluid	Fresh Water	Density	<b>8.33</b> Lb/Gal
Spacer type	Fresh Water	BBL.	<b>20</b> 8.33
Spacer type	Caustic	BBL.	<b>10</b> 8.40
Acid Type		Gal.	%
Acid Type		Gal.	%
Surfactant		Gal.	In
NE Agent		Gal.	In
Fluid Loss		Gal/Lb	In
Gelling Agent		Gal/Lb	In
Fric. Red.		Gal/Lb	In
MISC.		Gal/Lb	In

Hours On Location		Operating Hours		Description of Job
Date	Hours	Date	Hours	
3/11	15.0	3/11	4.0	Intermediate
Total	15.0	Total	4.0	

Perfpac Balls \_\_\_\_\_ Qty. \_\_\_\_\_  
Other \_\_\_\_\_  
Other \_\_\_\_\_  
Other \_\_\_\_\_  
Other \_\_\_\_\_  
Other \_\_\_\_\_

Pressures			
MAX	5000	AVG.	300
Average Rates in BPM			
MAX	8	AVG	5
Cement Left in Pipe			
Feet	91	Reason	SHOE JOINT

Cement Data						
Stage	Sacks	Cement	Additives	W/Rq.	Yield	Lbs/Gal
1	200	50/50 POZ PREMIUM	4% Gel - 0.4% C-12 - 0.1% C-37 - 0.5% C-41P - 2 lb/sk Phenoseal	6.77	1.44	13.60
2	0	0		0	0.00	0.00
3	0	0		0	0.00	0.00

Summary								
Preflush	<b>10</b>	Type:	CAUSTIC	Preflush:	BBI	<b>20.00</b>	Type:	FRESH WATER
Breakdown		MAXIMUM	5,000 PSI	Load & Bkdn:	Gal - BBI	N/A	Pad:Bbl -Gal	N/A
		Lost Returns-N	NO/FULL	Excess /Return	BBI	N/A	Calc.Disp Bbl	210
		Actual TOC	4,245	Calc. TOC:		4,245	Actual Disp.	210.00
Average		Bump Plug PSI:	980	Final Circ.	PSI:	540	Disp:Bbl	
ISIP	5 Min.	10 Min.	15 Min.	Cement Slurry:	BBI	51.3		
				Total Volume	BBI	281.29		

CUSTOMER REPRESENTATIVE \_\_\_\_\_ SIGNATURE \_\_\_\_\_



