



CEMENT

FOREMAN Fred Maden

REMARKS: Establish pump rate. Mix + Pump 100# Premium Gel Flush.
Mix + Pump 143 sks 50/50 Poz mix Cement 2% Gel 1/4" Flo Seal/sk.
Cement to Surface. Flush pump & lines clean. Displace 2 1/2"
rubber plug to casing TD. Pressure to 700 PSI. Release
pressure to set float valve. Short in casing.

Fred Moore

Հայկո 3797

DATE _____

acknowledge that the payment terms, unless specifically amended in writing on the front of the form or in the customer's account records, at our office, and conditions of service on the back of this form are in effect for services identified on this form.