

ATTACHMENT TO HORCHEM F-1 SWD WELL COMPLETION ACO-1

DEPTH		TYPE OF CEMENT	# SACKS USED	TYPE AND
TOP	BOTTOM			PERCENT ADDITIVES
1840	1902	Common	200	3% CC
920	1120	Common	100	3% CC
3505	3513	Common	150	3% CC
2448	3505	Common	50	3% CC
		Common	100	
3617	3730	Common	25	3% CC
2110	4555	Common	235	250# Hulls
1051		Common	15	
1048	1140	Micro	12	