

<b>JOB SUMMARY</b>			PROJECT NUMBER <b>SOK 2907</b>	TICKET DATE <b>07/24/13</b>
COUNTY <b>Sumner</b>	State <b>Kansas</b>	COMPANY <b>Bridge Exploration &amp; Produc</b>	CUSTOMER REP <b>Bruce Harper</b>	
LEASE NAME <b>Jesse 3204</b>	Well No. <b>1-33</b>	JOB TYPE <b>Surface</b>	EMPLOYEE NAME <b>Rickey Stephens</b>	

EMP NAME <b>Ricky Stephens</b>					
<b>Vontray</b>					
<b>Nate Cotta</b>					
<b>Brett Armer</b>					

Form. Name \_\_\_\_\_ Type: \_\_\_\_\_

Packer Type \_\_\_\_\_ Set At **0**

Bottom Hole Temp. **80** Pressure \_\_\_\_\_

Retainer Depth \_\_\_\_\_ Total Depth **350**

Date	Called Out <b>7/24/2013</b>	On Location <b>7/24/2013</b>	Job Started <b>7/24/2013</b>	Job Completed <b>7/24/2013</b>
Time	<b>09:30</b>	<b>12:30</b>	<b>18:30</b>	<b>20:00</b>

Type and Size	Qty	Make
Auto Fill Tube	0	IR
Insert Float Val	0	IR
Centralizers	0	IR
Top Plug	1	IR
HEAD	1	IR
Limit clamp	0	IR
Weld-A	0	IR
Texas Pattern Guide Shoe	0	IR
Cement Basket	0	IR

	New/Used	Weight	Size	Grade	From	To	Max. Allow
Casing		24#	8 1/2"		Surface	350	1,500
Liner							
Liner							
Tubing			0				
Drill Pipe							
Open Hole			12 1/4"		Surface	350	Shots/Ft.
Perforations							
Perforations							
Perforations							

Materials			
Mud Type	WBM	Density	Lb/Gal
Disp. Fluid	Fresh Water	<b>8.33</b>	
Spacer type	Fresh Water BBL.	<b>10</b>	<b>8.33</b>
Spacer type	BBL.		
Acid Type	Gal.	%	
Acid Type	Gal.	%	
Surfactant	Gal.	In	
NE Agent	Gal.	In	
Fluid Loss	Gal/Lb	In	
Gelling Agent	Gal/Lb	In	
Fric. Red.	Gal/Lb	In	
MISC.	Gal/Lb	In	
Perfpac Balls	Qty.		
Other			
Other			
Other			
Other			
Other			

Hours On Location		Operating Hours		Description of Job
Date	Hours	Date	Hours	
7/24	8.0	7/24	1.0	Surface
Total	8.0	Total	1.0	

Pressures	
MAX 1,500 PSI	AVG 200
Average Rates in BPM	
MAX 6 BPM	AVG 4
Cement Left in Pipe	
Feet 44	Reason SHOE JOINT

Cement Data						
Stage	Sacks	Cement	Additives	W/Rq.	Yield	Lbs/Gal
1	145	EX Lite Premium Plus 65 (6% Gel)	2% Calcium Chloride - 1/2pps Cello-Flake - .5% C-41P	10.88	1.84	12.70
2	50	Premium Plus (Class C)	2% Calcium Chloride - 1/2pps Cello-Flake	6.32	1.32	14.80
3	*100	Premium Plus (Class C)	*2% Calcium Chloride on side to use if necessary	*6.32	*1.32	*14.8

Summary					
Preflush Breakdown	Type: _____	MAXIMUM _____	Lost Returns-N _____	Actual TOC _____	Bump Plug PSI: _____
Average	ISIP _____	5 Min. _____	10 Min. _____	15 Min. _____	
Preflush:	BBI _____	Load & Bkdn: Gal - BBI _____	Excess /Return BBI _____	Calc. TOC: _____	Final Circ. PSI: _____
	10.00		40	SURFACE	200
				Cement Slurry: BBI _____	
				Total Volume BBI _____	
				59.3	89.30
Type: Fresh Water	Pad:Bbl -Gal _____	Calc. Disp Bbl _____	Actual Disp. _____	Disp:Bbl _____	
	N/A	20	20.00	20.00	

CUSTOMER REPRESENTATIVE \_\_\_\_\_ SIGNATURE \_\_\_\_\_





<b>JOB SUMMARY</b>			PROJECT NUMBER <b>SOK 2932</b>	TICKET DATE <b>08/02/13</b>
COUNTY <b>Sumner</b>	State <b>Oklahoma</b>	COMPANY <b>Sandridge Exploration &amp; Production</b>	CUSTOMER REP <b>Bruce Harper</b>	
LEASE NAME <b>Jesse 3204</b>	Well No. <b>1-33</b>	JOB TYPE <b>Production</b>	EMPLOYEE NAME <b>John Hall</b>	

EMP NAME	John Hall	Danny Tewell			
	Rocky Anthis				
	Joseph Klemm				
	Roy Morris				

Form. Name \_\_\_\_\_ Type: \_\_\_\_\_  
 Packer Type \_\_\_\_\_ Set At **0**  
 Bottom Hole Temp. **140°** Pressure \_\_\_\_\_  
 Retainer Depth \_\_\_\_\_ Total Depth **4,800'**

Date	Called Out <b>8/1/2013</b>	On Location <b>8/1/2013</b>	Job Started <b>8/2/2013</b>	Job Completed <b>8/2/2013</b>
Time	<b>2000</b>	<b>2330</b>	<b>200</b>	<b>400</b>

Type and Size	Qty	Make
Auto Fill Tube	0	IR
Insert Float Val	0	IR
Centralizers	0	IR
Top Plug	0	IR
HEAD	0	IR
Limit clamp	0	IR
Weld-A	0	IR
Texas Pattern Guide Shoe	0	IR
Cement Basket	0	IR

Well Data						
	New/Used	Weight	Size	Grade	From	To
Casing		17#	5 1/2"		Surface	
Liner						5,000
Liner						
Tubing			0			
Drill Pipe						
Open Hole			7 7/8"		Surface	4,800'
Perforations						Shots/Ft.
Perforations						
Perforations						

Materials			
Mud Type	WBM	Density	Lb/Gal
Disp. Fluid	Fresh Water	8.33	
Spacer type	BBL.		
Spacer type	Barite	15	10.00
Acid Type	Gal.		%
Acid Type	Gal.		%
Surfactant	Gal.		In
NE Agent	Gal.		In
Fluid Loss	Gal/Lb		In
Gelling Agent	Gal/Lb		In
Fric. Red.	Gal/Lb		In
MISC.	Gal/Lb		In
Perfpac Balls	Qty.		
Other			
Other			
Other			
Other			
Other			

Hours On Location		Operating Hours		Description of Job
Date	Hours	Date	Hours	
8/1	0.5	8/2	2.0	Production
8/2	5.0			
Total		Total		
5.5		2.0		

MAX	5,000 PSI	AVG.	
Average Rates in BPM			
MAX	5 BPM	AVG	
Cement Left in Pipe			
Feet	44	Reason	SHOE JOINT

Cement Data				Additives		
Stage	Sacks	Cement		W/Rq.	Yield	Lbs/Gal
1	500	50/50 POZ PREMIUM	4% Gel - 0.4% C-15 - 0.4% C-41P - 2pps Kalseal			
2	300	Premium	0.4% FL-17 - 0.1% C-20 - 0.4% C-41P	11.56	2.07	12.00
3	0	0		8.60	1.64	13.60
				0	0.00	0.00

Summary							
Preflush	15	Type:	Barite	Preflush:	BBI	15.00	Type: 10ppg Barite Spacer
Breakdown		MAXIMUM	5,000 PSI	Load & Bkdn:	Gal - BBI	N/A	Pad:Bbl -Gal N/A
		Lost Returns-N	NO/FULL	Excess /Return	BBI	N/A	Calc.Disp Bbl 110
		Actual TOC	Surface	Calc. TOC:		Surface	Actual Disp. 110.40
Average		Bump Plug PSI:	1.700	Final Circ.	PSI:	N/A	Disp:Bbl 110.40
ISIF	5 Min.	10 Min.	15 Min.	Cement Slurry:	BBI	271.9	
				Total Volume	BBI	397.30	

CUSTOMER REPRESENTATIVE Edwin Miller SIGNATURE