

<b>JOB SUMMARY</b>			PROJECT NUMBER <b>SOK 3335</b>	TICKET DATE <b>01/14/14</b>
COUNTY <b>Barber</b>	State <b>Kansas</b>	COMPANY <b>Bridge Exploration &amp; Produc</b>	CUSTOMER REP <b>Bill Tomlinson</b>	
LEASE NAME <b>Lambert 3014</b>	Well No. <b>1-34</b>	JOB TYPE <b>Surface</b>	EMPLOYEE NAME <b>marcos quintana</b>	

EMP NAME					
marcos quintana		0			
nate cotta					
walles berry					
flo falkelina					

Form. Name \_\_\_\_\_ Type: \_\_\_\_\_

Packer Type \_\_\_\_\_ Set At **0**

Bottom Hole Temp. **80** Pressure \_\_\_\_\_

Retainer Depth \_\_\_\_\_ Total Depth **1033**

Date	Called Out	On Location	Job Started	Job Completed
	<b>1/13/2014</b>	<b>1/13/2014</b>	<b>1/14/2014</b>	<b>1/14/2014</b>
Time	<b>1500</b>	<b>1950</b>	<b>500</b>	<b>630</b>

Tools and Accessories		
Type and Size	Qty	Make
Auto Fill Tube	0	IR
Insert Float Val	0	IR
Centralizers	0	IR
Top Plug	1	IR
HEAD	1	IR
Limit clamp	0	IR
Weld-A	0	IR
Texas Pattern Guide Shoe	0	IR
Cement Basket	0	IR

Well Data						
New/Used	Weight	Size	Grade	From	To	Max. Allow
Casing	36#	9 1/2"		Surface	1,033	1,500
Liner						
Liner						
Tubing		0				
Drill Pipe						
Open Hole		12 1/4"		Surface	1,033	Shots/Ft.
Perforations						
Perforations						
Perforations						

Materials			
	WBM	Density	Lb/Gal
Disp. Fluid	Fresh Water	Density	<b>8.33</b>
Spacer type	resh Wate BBL.	<b>10</b>	<b>8.33</b>
Spacer type	BBL.		
Acid Type	Gal.	%	
Acid Type	Gal.	%	
Surfactant	Gal.	In	
NE Agent	Gal.	In	
Fluid Loss	Gal/Lb	In	
Gelling Agent	Gal/Lb	In	
Fric. Red.	Gal/Lb	In	
MISC.	Gal/Lb	In	

Hours On Location		Operating Hours		Description of Job
Date	Hours	Date	Hours	
<b>1/13</b>	<b>9.0</b>	<b>1/14</b>	<b>1.5</b>	<b>Surface</b>
Total	<b>9.0</b>	Total	<b>1.5</b>	

Perpac Balls \_\_\_\_\_ Qty. \_\_\_\_\_

Other \_\_\_\_\_

Other \_\_\_\_\_

Other \_\_\_\_\_

Other \_\_\_\_\_

Pressures			
MAX	<b>1,500 PSI</b>	AVG.	<b>140</b>
Average Rates in BPM			
MAX	<b>6 BPM</b>	AVG	<b>5</b>
Cement Left in Pipe			
Feet	<b>44</b>	Reason	<b>SHOE JOINT</b>

Cement Data						
Stage	Sacks	Cement	Additives	W/Rq.	Yield	Lbs/Gal
<b>1</b>	<b>325</b>	<b>EX Lite Premium Plus 65</b>	<b>(6% Gel) 2% Calcium Chloride - 1/4pps Cello-Flake - .5% C-41P</b>	<b>11.11</b>	<b>2.01</b>	<b>12.40</b>
<b>2</b>	<b>125</b>	<b>Premium Plus (Class C)</b>	<b>2% Calcium Chloride - 1/4pps Cello-Flake</b>	<b>6.32</b>	<b>1.32</b>	<b>14.80</b>
<b>3</b>	<b>0</b>	<b>0</b>		<b>0.00</b>	<b>0.00</b>	<b>0.00</b>

Summary					
Preflush	<b>10.00</b>	Type:	Fresh Water		
Breakdown	<b>MAXIMUM 1,500 PSI</b>	Load & Bkdn:	Gal - BBI	<b>N/A</b>	Pad:Bbl -Gal <b>N/A</b>
	<b>Lost Returns-N</b>	Excess /Return	BBI	<b>77</b>	Calc. Disp Bbl <b>77</b>
	<b>Actual TOC</b>	Calc. TOC:		<b>SURFACE</b>	Actual Disp. <b>77.00</b>
Average	<b>Bump Plug PSI: 850</b>	Final Circ.	PSI:	<b>310</b>	Disp:Bbl
'SIP	<b>5 Min. 10 Min. 15 Min.</b>	Cement Slurry:	BBI	<b>145.7</b>	
		Total Volume	BBI	<b>232.73</b>	

CUSTOMER REPRESENTATIVE *Bill Tomlinson* SIGNATURE