



SandRidge Energy  
Murphy #3119 3-7H  
Comanche County, KS.

## 1.0 Executive Summary

Allied Oil & Gas Services would like to thank you for the award of the provision of cementing products and services on the well Murphy # 3119 3-7H Intermediate Casing.

A pre-job meeting was held to discuss job details, review the safety hazards, potential environmental impact and established emergency procedures.

Allied started the job testing lines to 3500 psi. After a successful test we began the job by pumping 30 bbls of preflush spacer. We then mixed and pumped the following cements:

60 Bbls (240 sacks) of 13.6 ppg Lead slurry:  
50:50 Class A:Poz Blend - 1.4 Yield  
2.0% Gel  
0.4% FL-160  
0.1% SA-51

21Bbls (100 sacks) of 15.6 ppg Tail slurry:  
Class A - 1.18 Yield  
0.8% FL-160  
0.2% CD-31

The top plug was then released and displaced with 224.75 of fresh water. The plug bumped and pressured up to 1300 psi. Pressure was released and floats held.

All real time data is shown on the graph in the attachment section.

Allied Oil & Gas Services remains committed to provide operational excellence and superior product performance. All comments and suggestions are greatly appreciated and help us to continue to provide this level of service.

Again we want to thank you for the opportunity to perform these and your future cementing & acidizing service needs.



SandRidge Energy  
Murphy #3119 3-7H  
Comanche County, KS.

## 1.0 Executive Summary

Allied Oil & Gas Services would like to thank you for the award of the provision of cementing products and services on the well Murphy #3119 3-7H Surface Casing.

A pre-job meeting was held to discuss job details, review the safety hazards, potential environmental impact and established emergency procedures.

Allied started the job testing lines to 2000 psi. After a successful test we began the job by pumping 10 bbls of preflush spacer. We then mixed and pumped the following cements:

120 Bbls (360 sacks) of 12.7 ppg Lead slurry:  
65:35 Class A:Poz Blend - 1.87 Yield  
6.0% Gel  
2.0%cc  
¼# Floseal

32 Bbls (150 sacks) of 15.6 ppg Tail slurry:  
Class A - 1.20 Yield  
2.0%cc  
¼# Floseal

The top plug was then released and displaced with 78 Bbls of fresh water. The plug bumped and pressured up to 800 psi. Pressure was released and floats held. Cement did Circulate.

All real time data is shown on the graph in the attachment section.

Allied Oil & Gas Services remains committed to provide operational excellence and superior product performance. All comments and suggestions are greatly appreciated and help us to continue to provide this level of service.

Again we want to thank you for the opportunity to perform these and your future cementing & acidizing service needs.