

Attached to and Made a Part of
ACO-1 Form for
WHITE EXPLORATION, INC.
HARTING #1
430' FSL and 1390' FWL
Section 7-4S-22W
Norton County, Kansas
API# 15-137-20732-00-00

Production Casing Cement

Bottom Stage cemented with 140 Sacks of Allied Special Blend Class A Cement with 6# of CA-200 (salt), 5.5% CA-500 (Gypseal), 2% gel and 5# Kol-Seal/sack.

Top Stage cemented with 300 sacks of Allied Light Blend Cement (65/35 Poz Mix) with 6% gel and .25lb/sk cellophane flakes. Cement circulated to surface.