

Job #: 10-16-7284

Anode Bed No. _____

Location: OneOK KS-KC-03

Load Date: 9/20/2017

Total Volts: 14.3

Total Amps: _____

Total Resistance Ω: _____

Top of Conducrete tagged at: 100 (ft.)

Commissioning Date: _____

Depth (ft.)	Anode #	Resistance (ohms)	Depth (ft.)	Anode #	Resistance (ohms)	Depth (ft.)	Anode #	Resistance (ohms)	Depth (ft.)	Anode #	Resistance (ohms)	Anode Output (amps)				
												Anode #	Depth (ft.)	No Conducrete	With Conducrete	
5			130		1.3	255		2.2	380							
10			135		2.0	260		2.6	385			1	287	4.40	5.70	
15			140		2.1	265		3.0	390			2	273	3.60	5.00	
20			145		1.9	270		3.2	395			3	259	3.60	4.30	
25	1.0		150		1.8	275		3.3	400			4	245	2.90	3.80	
30	1.6		155		1.7	280		3.6	405			5	231	2.30	4.30	
35	1.5		160		1.2	285		4.2	410			6	217	3.30	4.60	
40	2.0		165		1.0	290		4.4	415			7	203	3.20	4.30	
45	1.9		170		1.9	295		4.1	420			8	189	2.90	4.60	
50	1.7		175		1.8	300		3.9	425			9	175	2.60	4.40	
55	1.4		180		2.2	305			430			10	161	2.90	3.80	
60	1.2		185		2.1	310			435			11	147	2.20	3.00	
65	0.7		190		2.2	315			440			12	133	2.10	3.00	
70	0.8		195		2.3	320			445			13				
75	1.3		200		3.0	325			450			14				
80	1.5		205		2.8	330			455			15				
85	1.1		210		2.7	335			460			16				
90	1.5		215		2.9	340			465			17				
95	1.6		220		2.9	345			470			18				
100	1.9		225		2.8	350			475			19				
105	1.6		230		3.0	355			480			20				
110	1.7		235		3.1	360			485							
115	1.5		240		3.3	365			490							
120	1.1		245		3.1	370			495							
125	0.4		250		2.4	375			500							

Notes:

#'s Bentonite Used: 1880# PORTLAND CEMENT

Top of Conducrete tagged at: 101' on date: 8/21/2017
