

**Attachment to Wilson F-1 (API # 15-081-21948)**

**Cement & Additives**

String	Type	# of Sacks Used	Type and Percent Additives
Surface	A-Con	Lead: 390	3% CC, 1/4# Cellflake, 0.2% WCA1
	Prem +	Tail: 150	2% CC, 1/4# Cellflake
Production	50-50 Poz	290	5% W-60, 10% Salt, 0.6% C-15, 1/4# Defoamer, 5# Gilsonite 1/4# Polyflake