

TO: STATE CORPORATION COMMISSION  
CONSERVATION DIVISION - PLUGGING  
130 SOUTH MARKET, SUITE 2078  
WICHITA, KANSAS 67202

API Well Number: 15-079-34825-00-00  
Spot: NESWSW Sec/Twnshp/Rge: 8-22S-3W  
998 feet from S Section Line, 998 feet from W Section Line  
Lease Name: A R NIKKEL Well #: 2  
County: HARVEY Total Vertical Depth: 3466 feet

Operator License No.: 3942  
Op Name: MONROE, ORVILLE DBA BIG "O"  
Address: 2820 PASEO DRIVE  
GREAT BEND, KS 67530

PROD Size: 8.625 feet: 3153 150 SX CMT  
PROD Size: 5.5 feet: 3430 350 SX CMT  
SURF Size: 15.5 feet: 282 275 SX CMT

*112 65*

Well Type: OIL UIC Docket No: \_\_\_\_\_ Date/Time to Plug: \_\_\_\_\_  
Plug Co. License No.: 31529 Plug Co. Name: MIKE'S TESTING & SALVAGE, INC.  
Proposal Rcvd. from: ORVILLE MONROE Company: MIKE'S TESTING & SALVAGE, INC Phone: (620) 792-2868

Proposed Plugging Method: Sand to 3,100' and top with 5 sxs. cement. Shoot pipe off and pull same. Perforate 8 5/8" casing at 550' and 330'. Run tubing to 550' and spot 50 sxs. cement. Pull tubing to 330' and circulate cement to the surface inside and outside of 8 5/8" casing.

Plugging Proposal Received By: MICHAEL WILSON Witness Type: COMPLETE (100%)  
Date/Time Plugging Completed: 04/20/2004 2:00 PM KCC Agent: MICHAEL WILSON

Actual Plugging Report:

Sanded to 3,120' & topped with 5 sxs. cement. Shot 5 1/2" casing off at 1,230' & pulled same. Perforated 8 5/8" casing at 550' & 330'. Ran 2 3/8" tubing to 550' & spotted 50 sxs. cement. Pulled tubing to 327' & circulated 90 sxs. cement to surface. Tied on to 8 5/8" casing & pumped 140 sxs. cement. Cement did not circulate to surface on the backside of 8 5/8" casing. Ran 1" tubing, on the outside of 8 5/8" to 326' & spotted 50 sxs. cement. W.O.C. Ran wireline inside 8 5/8" to 570' & outside of 8 5/8" to 305'. Ran 1" tubing, on outside of 8 5/8", to 305' & spotted 50 sxs. cement w/3% CaCl. W.O.C. Ran 2 3/8" tubing, on outside of 8 5/8", to 307' & spotted 80 sxs. cement w/200 lbs. hulls & 3% CaCl. W.O.C. Ran 2 3/8" tubing, on outside of 8 5/8", to 276' and circulated 225 sxs. cement w/300 lbs. hulls to the surface. Ran 2 3/8" tubing, on the inside of 8 5/8", to 540' and circulated 155 sxs. cement to the surface.

Perfs:

Top	Bot	Thru	Comments
3154	3164		
RECEIVED KCC DISTRICT #2  APR 27 2004  WICHITA, KS			

Remarks: USED 840 SXS. 60/40 POSMIX W/4% GEL BY BY ALLIED CEMENTING CO. INC. INVOICE # 18272, 18273, & 18274.

Plugged through: TBG

District: 02

Signed Michael R Wilson  
**INVOICED** (TECHNICIAN)

DATE 5.5.04  
INV. NO. 2004061504